



## Technical Specification

### Bitumen 40/50

Specification	Test method		Result
Softening Point C	ASTM	D-36	52-60
Penetration @25 C	ASTM	D-5	40-50
Flash point C	ASTM	D-92	Min 250
Drop in penetration after heating %	ASTM	D-6D-5	Max 20

---

No. 4, Amdi St. Nelson mandela Blvd, Tehran15189 54714- Iran  
Tel: +98 21 88 77 31 24  
Fax: +98 21 88 78 09 63  
Email: [sales@varziran.com](mailto:sales@varziran.com)