



## Technical Specification

### Bitumen 85/100

Specification	Test method		Result
Softening Point C	EN	1427	46
Penetration @25 C	EN	1426	90
Specification gravity @25/25 C	ASTM	D-70	1.017
Flash point C	EN ISO	2592	305
Loss on heating ( wt )%	ASTM	1754	+0.038%
Drop in penetration after heating %	EN	1426	84%