



## Multi VARZSEAL® S-H/100

### Description

**MULTI VARZSEAL® SH/100** is a single component, hot-applied, plasto-elastic polymer modified bituminous Concrete Paving Joint crack and expansion joint Bridge sealant, specially formulated to be used into horizontal expansion Concrete joints and cracks. The sealant is supplied in solid form and can be applied using sealing melter applicator units.

---

### Uses

- Multistory parking decks
- Expansion joint in bridges and other concrete structures

---

### Advantages

Due to high polymer content, **MULTI VARZSEAL® SH/100** is viscous enough at application temperature to fill the cracks satisfactorily, and also is liquid enough to penetrate into all tiny holes of cracks and protecting them from penetrating water.

### General information

Color	Black
Bitumen type	Polymer-modified bitumen
Density	1±0.03 kg/l
Softening Point	~ 83 °C
Penetration	~ 75 dmm
Cone Penetration	~ 65 dmm
<b>Tensile adhesion</b>	<b>800%</b>
Maximum heating temperature	190 °C
Mixture temperature	170 ± 5 °C
Temperature in the nuzzle	160 to 165 °C
Packaging	14 kg pack



## Product Data Sheet

REV 98 Fall  
Page:2 of 2

# Multi VARZSEAL® S-H/100

## Application

<b>Crack configuration</b>	-Minimum Crack depth: -Width/Depth ratio:	10 mm 1/1.5
<b>Surface preparation</b>	All surfaces must be clean, dry and free from all loose adhering particles.	
<b>Heating</b>	Heat up to $170 \pm 5$ °C in a controlled oil bath or oil jacket melting-vessel with agitator until a smooth, even and pour able consistency is achieved.	
<b>Application</b>	Apply by melter-pourer or for detailed work use a metal-lipped bucket. Sealing may be done at environment temperature of 4°C and higher.	
<b>Cleaning</b>	Clean all tools and equipments immediately after use with Kerosene or other appropriate solvents	

## Safety Instructions

<b>Safety precautions</b>	Wear goggles and gloves during application. In case of contact with eyes immediately wash them with plenty of water and start first aids.
---------------------------	---