



Varziran CO.

Public Joint Stock

Technical Data Sheet

Emulsion Anionic **S**low **S**etting (SS-1)

PROPERTY	TEST METHOD	STANDARD RANGE	
		Min.	Max.
Test on Emulsion			
Residue, % W/W	ASTM D244	57	-
Viscosity , STV, @ 25°C , Sec.	BS2000-72	4	10
Sieve Test 0.850 mm. , W/W%	ASTM D244	-	0.1
Storage Stability , 24-h , %	ASTM D244	-	1
Particle Charge Test	ASTM D244	NEGATIVE	
Test on residue from distillation test			
Penetration , @25°C,100g,5s , 0.1 mm.	ASTM D5	100	200
Ductility @ 25°C,5cm/min , cm	ASTM D113	40	-
Solubility in trichloroethylene, %	ASTM D 2042	97.5	-

HEAD OFFICE: No. 4 Amid St. Nelson Mandela (Africa) Blvd., Tehran 15189-54714 IRAN
Tel.: (+98 21) 88773142, **Fax:** (+98 21) 88780963
E-mail: info@varziran.com **Website:** www.varziran.com
FACTORY: Shahid Beheshti Blvd., Najafabad Rd., Qazvin 34159-IRAN
Tel.: (+98 28) 333 43 888 , **Fax:** (+98 28) 333 49 680, Qazvin 34159