

Product Data Sheet

REV 98 Fall Page:1 of 2

VARZSEAL® S-H/10

Description

VARZSEAL® SH/10 is a single component, hot-applied, plasto-elastic polymer modified bituminous Concrete Paving Joint crack and expansion joint sealant, specially formulated to be used into horizontal expansion Concrete joints and cracks. The sealant is supplied in solid form and can be applied using sealing melter applicator units.

Uses

- -Concrete operon and Airport band
- -Concrete paving highways, runways and taxiways
- -Concrete roads
- -Multistory parking decks
- -Expansion joint in bridges and other concrete structures

Advantages

Due to high polymer content, VARZSEAL® SH/10 is viscous enough at application temperature to fill the cracks satisfactorily, and also is liquid enough to penetrate into all tiny holes of cracks and protecting them from penetrating water.

General information

Color	Black
Bitumen type	Polymer-modified bitumen
Density	1.1 -1.2 kg/l
Softening Point	~ +90 °C
Penetration	~ 32 dmm
Cone Penetration	~ 23 dmm
Maximum heating temperature	190 °C
Mixture temperature	170 ± 5 °C
Temperature in the nuzzle	160 to 165 °C
Packaging	16 kg pack



Product Data Sheet

REV 98 Fall Page:2 of 2

VARZSEAL® S-H/10

Application

Crack		
configuration	-Minimum Crack depth:	10 mm
J	-Width/Depth ratio:	1/1.5
Surface		
preparation	All surfaces must be clean, dry and free from all loose adhering particles.	
11		
Heating	Heat up to 170 ±5 °C in a controlled oil bath or oil jacket melting-vessel with	
	agitator until a smooth, even an	d pour able consistency is achieved.
Application		
• •	Apply by melter-pourer or for	detailed work use a metal-lipped bucket. Sealing
	may be done at environment ter	
Cleaning	•	-
•	Clean all tools and equipment	s immediately after use with Kerosene or other
	appropriate solvents	-

Safety Instructions

Safety				
precautions	Wear goggles and gloves during application. In case of contact with eyes			
immediately wash them with plenty of water and start first aids.				