



Technical Specification

Bitumen 115/15

Specification	Test method		Result
Softening Point C	BS 2000	Part 58	115±5
Penetration @25 C	BS 2000	Part 49	15±5
Loss on heating (wt)%	BS 2000	Part 45	0/5

No. 4, Amdi St. Nelson mandela Blvd, Tehran15189 54714- Iran

Tel: +98 21 88 77 31 24

Fax: +98 21 88 78 09 63

Email: sales@varziran.com