



Technical Specification

Bitumen 60/70

Specification	Test method		Result
Softening Point C	EN	1427	48
Penetration @25 C	EN	1426	66
Specification gravity @25/25 C	ASTM	D-70	1.004
Flash point C	EN ISO	2592	310
Loss on heating (wt)%	ASTM	1754	+0.02%
Drop in penetration after heating %	EN	1426	80%

No. 4, Amdi St. Nelson mandela Blvd, Tehran15189 54714- Iran
Tel: +98 21 88 77 31 24
Fax: +98 21 88 78 09 63
Email: sales@varziran.com